



# AeroShell Grease 6

AeroShell Grease 6 is a general purpose grease composed of a mineral oil thickened with Microgel®, possessing good all-round properties within a limited range. It is inhibited against oxidation and corrosion and has good water resistance and low noise capability. The useful operating temperature range is  $-40^{\circ}\text{C}$  to  $+121^{\circ}\text{C}$ .

## DESIGNED TO MEET CHALLENGES

### Main Applications

- AeroShell Grease 6 is a general purpose airframe grease for use in antifriction bearings, gearboxes and plain bearings within the temperature range of  $-40^{\circ}\text{C}$  to  $+121^{\circ}\text{C}$ .

### Specifications, Approvals & Recommendations

- U.S. : Approved MIL-PRF-24139A, Meets MIL-G-7711A (Obsolete)

- British : Approved DEF STAN 91-12
- French : Equivalent DCSEA 382/A
- NATO Code : G-382
- Joint Service Designation : XG-271

For a full listing of equipment approvals and recommendations, please consult your local Shell Technical Helpdesk.

### Typical physical Characteristics

Properties	MIL-PRF-24139A	Typical
Oil Type	Mineral	Mineral
Thickener Type	-	Microgel
Base Oil Viscosity @40°C mm <sup>2</sup> /s	-	35
Base Oil Viscosity @100°C mm <sup>2</sup> /s	-	5.5
Useful Operating Temperature Range °C	-	-40 to +121
Drop Point °C	149 min	260+
Worked Penetration @25°C	265 to 320	300
Unworked Penetration @25°C	-	287
Bomb Oxidation Pressure Drop 100 hrs @99°C lb/in <sup>2</sup>	10 max	9
Bomb Oxidation Pressure Drop 500 hrs @99°C lb/in <sup>2</sup>	25 max	15
Oil Separation 30 hrs @100°C % m	-	0.7
Water Resistance Test Loss @38°C % m	5 max	2
Evaporation Loss 22 hrs @121°C % m	-	1.3
Mean Hertz Load kg	30	35
Copper Corrosion 24 hrs @100°C	Must pass	Passes
Bearing Protection 2 days @51°C	Must pass	Passes
Anti-friction Bearing Performance @121°C hrs	-	2000+
Colour	-	Brown

These characteristics are typical of current production. Whilst future production will conform to Shell's specification, variations in these characteristics may occur.

## Health, Safety & Environment

- **Health and Safety**

Guidance on Health and Safety is available on the appropriate Material Safety Data Sheet, which can be obtained from <http://www.epc.shell.com/>

- **Protect the Environment**

Take used oil to an authorised collection point. Do not discharge into drains, soil or water.

## Additional Information

- **Advice**

Advice on applications not covered here may be obtained from your Shell representative.

